

LG SAN 80HF

LG Chem Ltd. - Styrene Acrylonitrile

Wednesday, November 27, 2024

General Information

Product Description

Description

High Transparency, Heat Resistance, Chemical Resistance

Application

Refrigerator Sleeves, Miscellaneous

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Latin America	
	• Europe	• North America	
Additive	• Mold Release		
Features	• Chemical Resistant	• High Clarity	• High Heat Resistance
Uses	• Electrical/Electronic Applications • Kitchenware		
Appearance	• Clear/Transparent		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	3.0	g/10 min	
220°C/10.0 kg	29	g/10 min	
230°C/3.8 kg	10	g/10 min	
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ² (3.20 mm)	3110	MPa	ASTM D638
Tensile Strength ³ (Yield, 3.20 mm)	73.5	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	6.0	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	3630	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	122	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.40 mm)	9.8	J/m	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 6.40 mm	92.0	°C	
Vicat Softening Temperature	100	°C	ASTM D1525 ⁵
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.6 mm	HB		
3.2 mm	HB		

UL LLC ©2024. All rights reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

LG SAN 80HF

LG Chem Ltd. - Styrene Acrylonitrile

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature	80	°C
Drying Time	2.0 to 4.0	hr
Minimum Moisture Content	0.0100	ppg
Rear Temperature	170 to 190	°C
Middle Temperature	180 to 200	°C
Front Temperature	190 to 210	°C
Nozzle Temperature	190 to 220	°C
Processing (Melt) Temp	190 to 220	°C
Mold Temperature	40 to 70	°C
Back Pressure	29.4 to 58.8	MPa
Screw Speed	30 to 60	rpm

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 1.0 mm/min
- ³ 50 mm/min
- ⁴ 15 mm/min
- ⁵ Rate B (120°C/h), Loading 2 (50 N)